

SIGRASIC® Performance

Material: Carbon fiber-reinforced silicon carbide (CSiC)
Application: High-temperature applications

Material data of SIGRASIC® Performance

Typical properties	Units	Performance
Density	g/cm ³	1.8
Flexural strength	MPa	260
Flexural modulus	GPa	60
Interlaminar shear strength	MPa	13
Max. application temperature	°C [°F]	1200 [2200] in vacuum or inert gas
Max. application temperature	°C [°F]	450 [840] in oxygen
Open porosity	%	2

Values without tolerance represent typical average values. For any engineering/design purposes please always contact our technical sales team.



Graphite Solutions | SGL CARBON GmbH
 Sales Europe/Middle East/Africa | cfrc-europe@sglcarbon.com
 Sales Americas | cfrc-americas@sglcarbon.com
 Sales Asia/Pacific | cfrc-asia@sglcarbon.com
www.cfrc-and-felts.com | www.sglcarbon.com

TDS CSiC-U.01
 07 2021/0 1NÄ Printed in Germany
 ®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".